


## Flame Retardant Fiberglass Tape



**Backing:** Coated Fiberglass Cloth

**Adhesive:** Rubber

**Liner:** N/A

**Colors:** White Printed

**Specifications:** Meets FAR 25.853(a) & 25.855(d), Airbus ABD0031, Para 7.3.2 and 7.4; Boeing 737-SL-25-115-B, 757-SL-25-085-B, 747-SL-25-195-B, 767-SL-25-112-B, 777-SL-25-037-B

**Standard Sizes:** 2" x 36yd, 72mm x 33M, 4"x36Yd

**NSN:** 7510-01-559-3419

### Applications

- Cargo pit applications for freight carrying aircraft
- Challenging applications where high adhesion and flame resistance is critical
- Seaming and repairing cargo compartment liners
- Covering pins & rivets

### Features

- Coated Fiberglass Cloth
- Rubber Based Adhesive
- Complies with FAR 25.853(a) & 25.855(d)

### Benefits

- Super high tensile strength
- Resists flame penetration for added safety
- High moisture resistance
- Coating protects skin from contacting fiberglass
- Aggressive adhesion to all surfaces
- Maintains seal under heavy loads
- Resists flagging and lifting
- Meets requirements for use in aircraft cargo compartments

### Physical Properties

	Standard UOM	Metric UOM	Test Method
<b>Total Thickness</b>	13 mils	330.2 mic	ASTM D-1000
<b>Adhesion to Steel</b>	38 oz/in	4.16 N/cm	PSTC-101
<b>Tensile Strength</b>	150 lb/in	262.69 N/cm	ASTM D-1000
<b>Operating Temperature</b>	40 to 200 °F	4 to 93 °C	
<b>Exiting Time</b>	0 sec		FAR 25.853(a)/25.855(d)
<b>Burn Length</b>	0.25"		FAR 25.853(a)
<b>Flame Penetration</b>	N/A		FAR 25.855(d)
<b>Drip Exiting</b>	N/A		FAR 25.853(a)
<b>After Glow</b>	0 sec		FAR 25.855(d)

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F  
 Standard Shelf Life (at 25C): 24 months from date of manufacture.

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.